



## Conductive agent

### Better BK-3080

#### *Product description:*

Better BK-3080 is an amine salt polymer, which has excellent conductivity in the added coating, reduces the surface resistance of the coating film, prevents the electrostatic condensation of the coating film, and prevents the dust adsorption on the coating film surface. It is applicable to the electrostatic spraying system.

#### *Product specification:*

appearance	Yellowish liquid
density	1.01
Active content%	98%
solvent	---

#### *Scope of application:*

Alkyd amino baking paint, acrylic amino baking paint, etc.

#### *Add amount and use method:*

It can be added at any stage of the production process. Due to different formulations and conditions, it is recommended that users determine the best dosage by experiments before use. The recommended dosage is 0.5~2.0% (total formula).

#### *Packaging and storage:*

When the temperature is low, there will be flocculation, which is normal. Please heat and melt it without affecting its effect.

25kg plastic bucket, 200kg iron bucket

#### *Heavy metal content:*

Sb	As	Ba	Cd	Cr	Pb	Hg	Se	Zn
<5	<2.5	<10	<5	<5	<5	<5	<5	<10