

wetting dispersant Better BWD-8190

Product Description

Better BWD-8190 It is a high molecular weight block copolymer solution containing pigment affinity groups with a 40% active content. BWD-8190 is a resin free, stable pigment concentrate specifically designed for the production of anti floating colored and anti blooming general water-based industrial coating systems. Free of organic solvents, suitable for water-based systems and printing inks.

It has a good dispersing effect on carbon black and organic pigments, and is suitable for both resin based and resin free systems. Providing excellent dispersibility to the system, effectively reducing its viscosity, especially providing excellent flowability and storage stability to the system.

Appearance	Transparent or slightly cloudy light yellow to					
	yellow liquid					
Solid content%	40					
Specific gravity (20 °C)	1.06 g/cm ³					
flash point	100°C					
acid value	10mgKOH/g					

Product specifications:

Application scope:

Waterborne pigment concentrate,

architectural/industrial/automotive/anti-corrosion coatings, printing inks, wood coatings, etc.

Recommended dosage: (The dosage depends on the diameter of the pigment, and the optimal dosage must be determined through a series of experiments)

pigment	%Dispersant activity				
inorganic pigment	20-30%				
Organic pigments	30-75%				
titanium dioxide	10-12%				
carbon black	50-150%				

Usage method:

In order to obtain the best performance, additives need to be slowly added (under stirring) to the mixture of grinding resin/cosolvent or lotion



resin. When used in resin free pigment concentrated slurry, it is necessary to mix the additives with water evenly before adding the pigment. The pigment must be slowly added after the additives are fully dispersed.

Packaging, transportation, and storage:

package: 25KG, 200KG/barrel.

Transportation: It belongs to the storage of non hazardous materials and can be transported as general chemicals.

Storage: Store this product in a cool and dry environment; Anti freezing and sun exposure; Under normal circumstances, the shelf life is one year.

Content	Sb	As	Ba	Cd	Cr	Pb	Hg	Se	Zn
ppm	<5	<2.5	<10	<5	<5	<5	<5	<5	<10

Heavy metal content: